

Lantor Coremat® XM

- The cost effective solution for open mould processes
- Is used as core material and/or print blocker
- Is a polyester nonwoven and compatible with all regular types of resins, including Polyester, Vinylester and Epoxy
- Is suitable for hand lay-up and spray-up processes

Applications Lantor Coremat® XM

- Marine: hulls, decks and structures of boats and yachts
- Transportation: parts and panels of cars, trailers, trucks and RV's
- Mass transit: interior and exterior of trains, light rail and buses
- Leisure: kayaks, surfboards, pools and tubs
- Industrial: cladding panels, containers and tanks
- Wind energy: nacelle covers and spinners

Properties		XM 2	XM 3	XM 4	XM 10
Thickness	mm	2,0	3,0	4,0	10,0
Roll length	m	80	50	40	15
Roll width	m	1	1	1	1
Dry weight	g/m²	80	110	140	250
Resin uptake	kg/m²	1,0	1,5	2,0	6,5
Density impregnated	kg/m³	540	540	540	680

Mechanical properties*	unit	value	test method	
Flexural strength	MPa	8,5	ASTM D790	
Flexural modules	MPa	1250	ASTM D790	
Tensile strength across layers	MPa	4	ASTM C297	
Compression strength: 10% strain	MPa	10	ISO 844	
Shear strength	MPa	3	ASTM C273-61	
Shear modules	MPa	25	ASTM C273-61	

^{*} Typical mechanical properties of Lantor Coremat XM 3 impregnated with unsaturated polyester resin

The information contained in this document has been compiled in good faith by Lantor BV, but nevertheless no representation or warranty is given as to the accuracy or completeness of the (technical) information provided herein. Lantor BV can not be held liable of any damages arising from any (printing) errors or omissions in this information. Lantor BV reserves the right to make changes with respect to the information provided at any time without further notice.

Information

Verlaat 22 - 3901 RG Veenendaal - The Netherlands

t +31 (0)318 537 111

e composites@lantor.com

enabling performance www.lantorcomposites.com

